

Facestock

A 50% hemp fibres, white uncoated, matt, woodfree printing paper. Wet strength, fungicidal treatments and good wet opacity. The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight 90 g/m 2 ISO 536 Caliper 110 μ m ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight 71 g/m 2 ISO 536 Caliper 62 μ m ISO 534

Laminate

Total Caliper 190 µm±10% ISO 534

Performance Data

Initial Tack 17 N/25mm FTM 9 Glass Peel Adhesion 90° 7 N/25mm FTM 2 St.St.

Min. Application Temp. 5 °C

Service Temperature -20 °C to 80 °C

Adhesive Performance

The adhesive features high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates. Specially designed for wine labelling applications it allows easy conversion of difficult label shapes.

Compliance and Approvals

The laminate is made with FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)


Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

CK169

Fasson ®

@HEMP PAPER50PCT FSC S2030-BG45WH FSC



HEMP PAPER 50% FSC

S2030

BG45WH FSC



The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty
All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2023 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.